



www.puffinpaint.com

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

NUCOLOUR WALLSEALER

Nucolour Wallsealer is a Water base acrylic base interior emulsion wall sealer paint that support hiding power, fast drying, and smooth matt finishing. This product is low odor and environment friendly.

Features

- Water based
- Low odour
- Better hiding power
- Fast drying
- Heavy Metal Free
- Matt finishing
- Better hiding power
- Environment friendly

Recommended use

Wall sealer for interior

Film thickness and spreading rate	Minimum	Maximum	Typical
Film thickness, dry (um)	27	40	35
Film thickness, wet (um)	80	150	120
Theoretical spreading rate	3	6	4(m ² / l)

Physical properties

Color	White
Solids	(Vol %)*30%
Flash point	Nonflammable



www.puffinpaint.com

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

=====

Application methods

Roller	Recommended
Brush	Recommended
Spray	Airless spray or conventional spray
Mixing ratio (volume)	The paint is ready to use after proper stirring. If thinning is required clean water may be added up to a maximum of 20 %

Guiding data airless spray

Pressure at nozzle	140-190 kg/cm ² (2100psi)
Nozzle tip	0.021"-0.027"
Spray angle	65'-80'
Filter	Check to ensure that filters are clean
Drying time	Drying time are generally related to air circulation, temperature, film thickness, and number of coats, and will be affected correspondingly.

The figures given in table are typical with:

- Good ventilation (outdoor exposure of free circulation of air)
- Typical film thickness
- One coat on top of inert substrate
- Relative humidity 70 %



www.puffinpaint.com

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

Substrate temperature	10'C	23'C	40'C
Surface dry	4 h	30min	10 min
Through dry	8 h	4 h	1 h
Dry to re coat minimum 1	1h	30 min	15 min

Dry to recoat minimum 2, 3

1. In case of multicoat application, drying time will be influenced by the number and sequence and by total thickness of previous coats applied-reference is made to corresponding system data sheet
2. The surface should be dry and free from any contamination prior application of subsequent coat

The given data must be considered as guidelines only, the actual of drying time /time before re coating may be shorter or longer depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameter and special condition could be included.

Typical paint system	Interior
Nucolour wallsealer	1-2 coat
Topcoat Nucolor	2-3 coat
	Other system may be specified depending on area of use

Surface Preparation	All surfaces must be thoroughly cleaned and free of all dirt, dust, grease, loose or flaking paint. Efflorescence or mold on masonry or concrete surfaces must be treated. Occasionally an apparently sound old paint will lose adhesion when recoated, particularly if the new paint is darker in color. To avoid this, check the adhesion of the old paint by cutting an 'X' through a clean area of the film with a sharp blade, press cellulose tape firmly across the cut
---------------------	--



www.puffinpaint.com

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

and rip if off. If the old paint comes off with the tape it should be removed before repainting

Clean Up

Clean all equipment with water

Condition during application

Apply at a temperature between 10°C and 35°C, Temperature of substrate should be minimum 3°C above the dew point of the air, the temperature and relative humidity should be measured in vicinity of substrate

Storage

The product must be stored in tightly closed container and keep container in dry cold, well ventilation space, away from source of heat and ignition.

Handling

Handle with care, stir well before use

Packing

5Kg & 25Kg