

## NUCOLOUR CEILING

NUCOLOUR CEILING is a low odor and environment friendly modified acrylic base interior ceiling emulsion paint. This product is suitable for gypsum substrate (ceiling and gypsum walls)

### Features

- Water based
- Low VOC
- Formaldehyde Free
- Heavy Metal Free
- APEO Free
- Carbendazim free
- Matt finishing
- Low odor
- Better hiding power
- Environment friendly

### Recommended use

Use as top coat for interior gypsum substrate

Film thickness and spreading rate	Minimum	Maximum	Typical
Film thickness, dry (um)	50	60	55
Film thickness, wet (um)	100	120	76
Theoretical spreading rate (m <sup>2</sup> /l)	10	8	9



[www.puffinpaint.com](http://www.puffinpaint.com)

# PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

---

## Physical properties

Color	White
Solids	(Vol %)* 52+/-2
Flash point	Nonflammable
Water resistant	Good
Sanding properties	Excellent

## Application methods

Roller	Recommended
Brush	Recommended
Spray	Use airless spray or conventional spray

## Application data

Mixing ratio (volume)	The paint is ready to use after proper stirring if thinning is required water may be added up to a maximum of 20%.
Thinner/ cleaner	Water

## Guiding data airless spray

Pressure at nozzle	140-190 kg/cm <sup>2</sup> (2100psi)
Nozzle tip	0.021"-0.027"
Spray angle	65'-80'
Filter	Check to ensure that filters are clean



[www.puffinpaint.com](http://www.puffinpaint.com)

# PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

Drying time

Drying time are generally related to air circulation, temperature, film thickness, and number of coats, and will be affected correspondingly.

The figures given in table are typical with:

- Good ventilation (outdoor exposure of free circulation of air)
- Typical film thickness
- One coat on top of inert substrate
- Relative humidity 70 %

Substrate temperature	10'C	23'C	40'C
Surface dry	2h	1 h	0.5 h
Through dry	8h	6h	4h
Dry to recoat minimum 1	4h	2h	1h

Dry to recoat minimum 2, 3

1. Recommended data given for re coating with the same generic type of paint
2. In case of multi coat application, drying time will be influenced by the number and sequence and by total thickness of previous coats applied-reference is made to corresponding system data sheet
3. The surface should be dry and free from any contamination prior application of subsequent coat

The given data must be considered as guidelines only, the actual of drying time /time before re coating may be shorter or longer depending on film thickness, ventilation, humidity, under lying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameter and special condition could be included.

Typical paint system

Nucolour ceiling 2-3 coat gypsum substrate

Other system may be specified depending on area of use

Surface Preparation

All surfaces must be thoroughly cleaned and free of all dirt, dust, grease, lose or flaking paint. Efflorescence or mold on masonry or

Technical Data Sheet



[www.puffinpaint.com](http://www.puffinpaint.com)

---

## PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

---

concrete surfaces must be treated.

Occasionally an apparently sound old paint will lose adhesion when recoated, particularly if the new paint is darker in color. To avoid this, check the adhesion of the old paint by cutting an 'X' through a clean area of the film with a sharp blade, press cellulose tape firmly across the cut and rip it off. If the old paint comes off with the tape it should be removed before repainting.

Clean Up

Clean all equipment with water

Condition during application

Apply at a temperature between 10°C and 35°C, Temperature of substrate should be minimum 3°C above the dew point of the air, the temperature and relative humidity should be measured in vicinity of substrate

Storage

The product must be stored in tightly closed container and keep container in dry cold, well ventilation space, away from source of heat and ignition.

Handling

Handle with care, stir well before use

Packing size

5kg & 25kg