



www.puffinpaint.com

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

PUFFIN EPOXY BC CHEMICAL RESISTANT 40%

Two component cycloaliphatic amine cured phenolic /novolac epoxy with gloss finishing. This product is high performance body coat for chemical resistant floor epoxy coatings system

1. Properties

COLOR	Limited color
GLOSS LEVEL	gloss (45-75)
FILM THICKNESS, DRY (μm)	500-2000
FILM THICKNESS, WET (μm)	500-2000
THEORETICAL SPREADING RATE (M^2/L)	2-0.5
SOLIDS (VOL %)	75% +/- 2
DENSITY (g/cm^3)	1.4
FLASH POINT	100C \pm 2%
PRACTICAL COVERAGE	ALLOW APPROPRIATE LOSS FACTORS

2. Characteristics

Floor

water and chemical resistant epoxy system,
with chemical exposed up to 40%
concentrate acidic

3. Usage

1) Surface preparation:

Clean, dry and free from undamaged
compatible coatings.

2) Substrate Minimum Recommended:

The The surface must be dry, free from
dust and other contaminant.

3) Application:

Spray recommended:

Airless spray, airspray, brush, roller
Pressure at nozzle (minimum): 150
bar/2100 psi
Nozzle tip (inch/1000): 15-19



www.puffinpaint.com

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

Brush Recommended:

Filter Check to ensure that filters are clean.

For stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.

4) Mixing ratio

Base A:

4

Base B:

1

5) Drying and Curing time:

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Walk-on-dry:

Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum:

The shortest time allowed before the next coat can be applied.

Surface (touch) Dry:

The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

SUBTRATE TEMPERATURE (°C)	15	23	40
SURFACE DRY (hour)	6	4	2
DRY ON WALK (hours)	24	15	6
Dry to over coat, minimum (hours)	24	15	6
Dry to over coat, minimum (hours)	72	36	24
Dryed/cured for service (days)	10	7	3



www.puffinpaint.com

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

6) Product compatibility:

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product.

Some examples are shown below.

Previous:

Epoxy

Subsequent coat:

Epoxy, Polyurethane

4. Precaution

1) Ensure to clean the surface before application.

2) Health and safety :

Please observe the precautionary notices displayed on the container.

Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact.

Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

3) Storage:

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care. Shelf life at 23 °C : 24 Month(s)

5. Packing size:

20 Kg Set