



www.puffinpaint.com

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

PUFFIN SPORTCO

Is an acrylic base interior exterior emulsion floor paint which is suitable for sport arena. This product has good adhesion to concrete or asphalt

Features

- Water based
- High ph for good penetration in wet substrate
- Doff finishing
- Fast dry
- Environment friendly

Recommended use

Top coat for interior and exterior floor at sport arena. Suitable for new or previously painted interior concrete masonry, plaster and brickwork.

Film thickness and spreading rate	Minimum	Maximum	Typical
Film thickness, dry (um)	150	200	200
Film thickness, wet (um)	250	420	333
Theoretical spreading rate (10 cm line width/ l)	26	16	20

Physical properties

Color	as per colour card
Solids (vol %)*	55+/-2
Flash point	Nonflammable



www.puffinpaint.com

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

Water resistant

good

Sanding properties

excellent

Application methods

Roller

Recommended

Brush

Recommended

Spray

Use airless spray or conventional spray

Application data

Mixing ratio (volume)

The paint is ready to use after proper stirring. If thinning is required, water may be added up to a maximum of 10%

Thinner/ cleaner

Water

Guiding data airless spray

Pressure at nozzle

140-190 kg/cm² (2100psi)

Nozzle tip

0.021"-0.027"

Spray angle

65'-80'

Filter

check to ensure that filters are clean

Drying time

Drying time are generally related to air circulation, temperature, film thickness, and number of coats, and will be affected correspondingly.

The figures given in table are typical with:

- Good ventilation(outdoor exposure of free circulation of air
- Typical film thickness
- One coat on top of inert substrate
- Relative humidity 70 %



www.puffinpaint.com

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

Substrate temperature	10'C	23'C	40'C
Surface dry (minuted)	45	30	15
Through dry (hour)	2	1.5	1
Dry to re coat minimum (Hour)	24	1.5	1
Dry to full cured (days)	7	4	3

1. Recommended data given for recoating with the same generic type of paint
2. In case of multi coat application ,drying time will be influenced by the number and sequence and by total thickness of previous coats applied-reference is made to corresponding system data sheet
3. The surface should be dry and free from any contamination prior application of subsequent coat

The given data must be considered as guidelines only, the actual of drying time /time before re coating may be shorter or longer depending on film thickness, ventilation ,humidity ,underlying paint system, requirement for early handling and mechanical strength etc, a complete system can be described on a system sheet ,where all parameter and special condition could be included.

Typical paint system	Exterior
Puffin Primer Sportco	1 coat
Puffin Sportco	2 coat

Other system may be specified depending on area of use

Surface Preparation

All surfaces must be thoroughly cleaned and free of all dirt, dust, grease, loose or flaking paint. Efflorescence or mould on masonry or concrete surfaces must be treated. Occasionally an apparently sound old paint will lose adhesion when recoated, particularly if the new paint is darker in color. To avoid this, check the adhesion of the old paint by cutting an 'X' through a clean area of the film with a sharp blade, press cellulose tape firmly across the cut and rip if off. If the old paint comes off with



www.puffinpaint.com

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

Clean Up

the tape it should be removed before repainting.

Clean all equipment with water

Condition during application

Apply at a temperature between 10°C and 35°C, Temperature of substrate should be minimum 3°C above the dew point of the air, the temperature and relative humidity should be measured in vicinity of substrate

Storage

The product must be stored in tightly closed container and keep container in dry cold, well ventilation space, away from source of heat and ignition.

Handling

Handle with care, stir well before use

Packing size

5 kg / 25 Kg Set (include silica sand)