



[www.puffinpaint.com](http://www.puffinpaint.com)

# PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

## PUFFIN EPOXY SEMI SELF LEVELING

Two or three component cycloaliphatic amine cured epoxy. This product have high performance of top coat floor coatings, this product reduced seamless surface, high gloss, chemical resistant, suitable for high build floor coatings system. Also available for antiskid mortar top coat.

### 1. Properties

COLOR	Limited colour
GLOSS LEVEL	gloss (75-85)
FILM THICKNESS, DRY ( $\mu\text{m}$ )	300-1000
FILM THICKNESS, WET ( $\mu\text{m}$ )	300-1000
THEORETICAL SPREADING RATE ( $\text{M}^2/\text{L}$ )	3-1
SOLIDS (VOL %)	80% +/- 2
DENSITY ( $\text{g}/\text{cm}^3$ )	1.3
FLASH POINT	100°C $\pm$ 2%
PRACTICAL COVERAGE	ALLOW APPROPRIATE LOSS FACTORS

### 2. Characteristics

1) Recommended

For wide range floor coatings system, with various level of mechanical and chemical exposure, industrial, factory, laboratory, hospital, ware house, hangar, food and beverage plant, kitchen, and etc. Available anti skid epoxy mortar system with thickness >1000 micron

### 3. Usage

1) Surface preparation:

Clean, dry and free from undamaged compatible coatings.

2) Substrate minimum recommended

The surface must be dry, free from dust and other contaminant.

3) Application:

Raskam, brush, roller and spike roll



[www.puffinpaint.com](http://www.puffinpaint.com)

# PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

#### 4) Mixing ratio

Base A :	4
Base B :	1
Base C :	as coarse need

#### 5) Drying and Curing time:

Drying and curing times are determined undercontrolled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The shortest time allowed before the next coat can be applied.

Surface (touch) Dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

SUBTRATE TEMPERATURE (°C)	15	23	40
SURFACE DRY (hour)	6	4	2
DRY ON WALK (hours)	24	15	6
Dry to over coat, minimum (hours)	24	15	6
Dry to over coat, minimum (hours)	72	36	24
Dryed/cured for service (days)	10	7	3



[www.puffinpaint.com](http://www.puffinpaint.com)

# PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

=====

6) Product compatibility: Depend on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product.

Some examples are shown below.

Previous : Epoxy

Subsequent coat: Epoxy, polyurethane

#### 4. Precaution

1) Ensure to clean the surface before application.

2) Health and safety :

Please observe the precautionary notices displayed on the container.

Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact.

Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

3) Storage :

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care. Shelf life at 23 °C : 24 Month(s)

#### 5. Packing size:

1kg, 5kg & 20kg Set



[www.puffinpaint.com](http://www.puffinpaint.com)

PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

---