



[www.puffinpaint.com](http://www.puffinpaint.com)

# PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

## PUFFIN EPOXY PRIMER

Two component polyamide cured epoxy ( solvent free ).This product has very good adhesion for most of concrete. It can be use in normal condition. Suitable for floor coatings system on concrete for floor or wall

### 1. Properties.

COLOR	Transparent grey
GLOSS LEVEL	gloss (70-80)
FILM THICKNESS, DRY (µm)	100-200
FILM THICKNESS, WET (µm)	100-200
THEORETICAL SPREADING RATE (M <sup>2</sup> /L)	5-10
SOLIDS (VOL %)	98% +/- 2
DENSITY (g/cm <sup>3</sup> )	1.4
FLASH POINT	18°C ± 2%
PRACTICAL COVERAGE	ALLOW APPROPRIATE LOSS FACTORS

### 2. Characteristics

1) Recommended for

Floor and wall concrete primer  
Suitable for all puffin epoxy floor coatings system (multi layer, semi self leveling, self leveling)

### 3. Usage

1) Surface preparation:

Sand blasting or diamond grinding concrete until free from old coatings, porous concrete and free from contamination material such us oil, silicon and other rustic chemical

2) Substrate minimum recommended :

The surface must be dry, free from dust



[www.puffinpaint.com](http://www.puffinpaint.com)

# PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

porous concrete, water and other contaminant, minimum 4 week curing moisture content maximum 5% with harness min 300 K.

3) Application:

Brush, roller

4) Mixing ratio

Base A :

4

Base B :

1

Drying and Curing time:

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product

Walk-on-dry:

Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum:

The shortest time allowed before the next coat can be applied.

Surface (touch) Dry:

The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

SUBTRATE TEMPERATURE (°C)	15	23	40
SURFACE DRY (hour)	7	5	3
DRY ON WALK (hours)	25	16	9
Dry to over coat, minimum (hours)	24	15	6
Dry to over coat, minimum (hours)	72	48	30
Dryed/cured for service (days)	10	7	4



[www.puffinpaint.com](http://www.puffinpaint.com)

=====

# PT. Indowijaya Sakti Teguh

Jl. Pangeran Jayakarta 121/3-4

Telp : 021- 62313238

5) Product compatibility:

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product.

Some examples are shown below.

Subsequent coat:

Epoxy, polyurethane

## 4. Precaution

1) Ensure to clean the surface before application.

2) Health and safety :

Please observe the precautionary notices displayed on the container.

Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact.

Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Storage :

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care. Shelf life at 23 °C : 24 Month(s)

5. Packing size

1kg, 5kg & 20kg Set